

TECHNICAL DATA SHEET

CSR-1303-FRY Yellow Flame Resistant Reflective Fabric

DESCRIPTION

Chinastars reflective fabric CSR-1303-FRY is composed of retro reflective micro-glass beads layer and fluorescent yellow stratum laminated onto a flame retardant cotton fabric. It reflects light directly to the original light source and enhances the visibility of anyone who wears it.

REFLECTIVE PERFORMANCE

The reflective coefficient (R, in cd/lux/m²) of CSR-1303-FRY yellow flame resistant fabric :

Observation Angle	Entrance Angle	Typical Reflectivity
12'	5°	>10

COLOR

Product No.	Daytime Color
CSR-1303-FRY	Fluorescent Yellow

CERTIFICATION

CSR-1303-FRY Yellow flame resistant reflective fabric meet the requirements in below listed standards for high visibility garments.

Product No.	EN 469 EN ISO 14116 EN ISO 11612 NFPA 701 ASTM F1506
CSR 1303-FRY	✓

APPLICATION INSTRUCTIONS

Cutting: Die-cutting is recommended, although it can also be hand-cut or guillotined.

Sewing: Sew in place using a lockstitch with no more than 12 stitches per inch (2.54 cm), and not less than 5/64" (2 mm) from the edge of the reflective fabric. For best results, apply to light and medium weight fabrics.

Printing: Inks can be printed on the surface of Chinastars reflective fabrics. Before printing, all inks shall be tested to ensure acceptable adhesion. Wipe the surface lightly with a soft cloth dampened with isopropyl alcohol may help ink adhesion.

CARE AND MAINTENANCE INSTRUCTIONS

Actual life of CSR-1303-FRY yellow fabric trim depends on cleaning method and wear conditions.



Do not presoak
Machine wash warm,
60°C (140°F)



Tumble
dry low



Cool iron, Do
not exceed
110°C(230°F)



Do not bleach

Some suggestions for extending the life of reflective fabric on safety clothing:

1. When do machine wash, you may use a mild detergent, but No Bleach or Fabric Softener!
2. Try to avoid wash the reflective products with your work jeans or any clothing with rough fabric or edges. The microscopic glass beads on the reflective fabric can be worn off by rough texture.
3. Try to line dry your reflective products. If you choose to machine dry, try to remove the product immediately. The added heat can damage the reflective fabric.

HANDLING PRECAUTIONS

Most of our reflective fabric contains aluminum layer, and sweat /oil/ water stains may occur if the surface of the product has direct contact with hands during application and is then exposed to hot and humid conditions. Even though these blemishes won't affect performance of the product, we strongly recommend handling the reflective fabric with gloves and keeping them in the environment of below 26.7 °C (80 °F) and lowering than 70% relative humidity.



ZHEJIANG CHINASTARS NEW MATERIALS GROUP CO., LTD

Office: No.98 Shimin Street, Shangcheng District,
Hangzhou, China, 310016
Tel: Fax: +86-571-88155512
Website: +86-571-88156171
Email: www.chinareflective.com
info@chinastars.com.cn

Hangzhou Factory:
Jingshan Town,
Yuhang district,
Hangzhou, China

Huzhou Factory:
Southern Industrial
Park, Changxing
county, Huzhou, China
BE SEEN, BE SAFER