



TECHNICAL DATA SHEET

Chinastars reflective fabrics

DESCRIPTION

Chinastars reflective fabrics are composed of micro-glass beads embedded into base fabric such as polyester, TC, FR cotton, aramid or spandex fabric, etc. It reflects light directly to the original light source and enhances the visibility of anyone who wears it. Chinastars Reflective fabrics have excellent durability in home wash, dry cleaning and industrial wash to meet various requirements of occupational apparel.

Product No.	Backing Fabric	Retro Reflective performance ¹	Home Wash Cycles ²	Dry cleaning Cycles ³	Industrial wash Cycles ⁴
CSR-1303-2 Grey fabric	100% Polyester	R>330	>25	—	—
CSR-1304-4 Grey fabric	65% Polyester and 35% Cotton	R>330	>25	—	—
CSR-1303-5 Silver fabric	100% Polyester	R>420	>25	—	—
CSR-1303-6 Silver fabric	65% Polyester and 35% Cotton	R>420	>50	—	—
CSR-1325 Silver fabric	65% Polyester and 35% Cotton	R>420	>100	—	—
CSR-6660 Silver fabric	100% Polyester	R>420	>50	>50	>50
CSR-1303-8 Silver stretchable fabric	86% Polyester and 14% Spandex	R>420	>25	—	—
CSR-1303-9 Silver stretchable fabric	86% Polyester and 14% Spandex	R>420	>25	—	—
CSR-1303-FR Silver flame resistant fabric	100% FR treated Cotton	R>420	>50	>50	—
CSR-1303-FR2Y Yellow-silver flame resistant fabric	100% FR treated Cotton	R>420	>50	>50	—
CSR-1303-FR2O Orange-silver flame resistant fabric	100% FR treated Cotton	R>420	>50	>50	—
CSR-1303-NM Silver flame resistant fabric	100% Aramid	R>420	>50	>50	—
CSR-1303-NM2Y Yellow-silver flame resistant fabric	100% Aramid	R>420	>50	>50	—
CSR-1303-NM2O Orange-silver flame resistant fabric	100% Aramid	R>420	>50	>50	—

¹ Measured on new product at +5.0° entrance and 0.2° observation angles

² ISO 6330 Method 6N at 60 °C (140 °F) and $R_A \geq 100$ cd/lux/m² (home wash)

³ ISO 3175 Method 8.1 and $R_A \geq 100$ cd/lux/m²

⁴ ISO 15797:2002 at 75 °(165 °F) and $R_A \geq 100$ cd/lux/m²

PRODUCT CERTIFICATION

The following Chinastars reflective fabrics meet the requirements for reflective material in below listed standards for high visibility garments.

Product No.	OKEO-TEX 100	EN ISO 20471 ANSI/ISEA 107 CSA-Z96-22 AS/NZS 1906	EN 469 EN ISO 14116 EN ISO 11612 NFPA 701 ASTM 1506
CSR-1303-2 Grey fabric	✓	✓	N/A
CSR-1303-4 Grey fabric	✓	✓	N/A
CSR-1303-5 Silver fabric	✓	✓	N/A
CSR-1303-6 Silver fabric	✓	✓	N/A
CSR-1325 Silver fabric	✓	✓	N/A
CSR-6660 Silver fabric	✓	✓	N/A
CSR-1303-8 silver stretchable fabric	✓	✓	N/A
CSR-1303-9 silver stretchable fabric	✓	✓	N/A
CSR-1303-FR Silver flame resistant fabric	—	✓	✓
CSR-1303-FR2Y Yellow-silver flame resistant fabric	—	✓	✓
CSR 1303-FR2O Orange-silver flame resistant fabric	—	✓	✓
CSR-1303-NM Silver flame resistant fabric	—	✓	✓
CSR-1303-NM2Y Yellow-silver flame resistant fabric	—	✓	✓
CSR-1303-NM2O Orange-silver flame resistant fabric	—	✓	✓

PHYSICAL PERFORMANCE

After the following each exposure testing, Chinastars reflective fabrics R_A values are above 100 cd/lux/m² at +5.0° entrance angle and 0.2° observation angle.

Physical performance	Test method
Abrasion	EN 530 Method 2, 5000 cycles
Flexing	ISO 7854 Method A, 7500 cycles
Cold Fold	ISO 4675, -20°C (-4°F)
Temperature Cycle	12 hours at 50 °C (122 °F); 20 hours at -30°C (-22°F)
Wash	ISO 6330 Method 6N at 60°C (140°F) number of cycles listed
Dry-Clean	ISO 3175 Method 9.1 number of cycles listed
Wet Reflectivity	ANSI 107-2020 Appendix B; EN 20471:2013 Annex C
Flame Resistance	ASTM D6413 char length ≤4 inches; after flame <2 seconds

APPLICATION

Cutting: Die-cutting is recommended, although it can also be hand-cut or guillotined.

Sewing: Sew in place using a lockstitch with no more than 12 stitches per inch (2.54 cm), and not less than 5/64" (2 mm) from the edge of the reflective fabric. For best results, apply to light and medium weight fabrics.

Printing: Inks can be printed on the surface of Chinastars reflective fabrics. Before printing, all inks shall be tested to ensure acceptable adhesion. Wipe the surface lightly with a soft cloth dampened with isopropyl alcohol may help ink adhesion.

Product	Wash	Dry	Iron
CSR-1303-2 grey fabric	 Do not presoak Machine wash warm, 40°C (105°F)  Do not bleach  Do not dry-clean	 Tumble dry low	 Cool iron, do not exceed 120°C (248°F)
CSR-1303-4 grey fabric			
CSR-1303-5 silver fabric			
CSR-1303-6 silver fabric			
CSR-1325 silver fabric			
CSR-1303-8 stretchable fabric			
CSR-1303-9 stretchable fabric			
CSR-6660 industrial wash fabric	 Do not presoak Machine wash warm, 60°C(140°F)  Do not bleach	 Tumble dry low	 Cool iron, do not exceed 150°C (300°F)
CSR-1303-FR flame resistant fabric			
CSR-1303-FR2Y flame resistant fabric			
CSR-1303-FR2O flame resistant fabric			
CSR 1303-NM flame resistant fabric			
CSR-1303-NM2Y flame resistant fabric			
CSR-1303-NM2O flame resistant fabric			

Some suggestions for extending the life of reflective fabric on safety clothing:

1. When do machine wash, you may use a mild detergent, but No Bleach or Fabric Softener!
2. Try to avoid wash the reflective products with your work jeans or any clothing with rough fabric or edges. The microscopic glass beads on the reflective fabric can be worn off by rough texture.
3. Try to line dry your reflective products. If you choose to machine dry, try to remove the product immediately. The added heat can damage the reflective fabric.

HANDLING PRECAUTIONS

Most of our heat transfer film contains aluminum layer, and sweat /oil/ water stains may occur if the surface of the product has direct contact with hands during application and is then exposed to hot and humid conditions. Even though these blemishes won't affect performance of the product, we strongly recommend handling the reflective fabric with gloves and keeping them in the environment of below 26.7 °C (80 °F) and lowering than 70% relative humidity.



ZHEJIANG CHINASTARS NEW MATERIALS GROUP CO., LTD

Office: No.98 Shimin Street,Shangcheng District,
Hangzhou,China,310016
Tel: Fax: +86-571-88155512
Website: +86-571-88156171
Email: www.chinareflective.com
info@chinastars.com.cn

Hangzhou Factory:
Jingshan Town,
Yuhang district,
Hangzhou,China

Huzhou Factory:
Southern Industrial
Park, Changxing
county, Huzhou,China
BE SEEN, BE SAFER